

ZOTA PAINT

# ZOTA EPON FINISH 303 Technical Data Sheet

#### **DESCRIPTION :**

ZOTA EPON FINISH 303 is a two-pack epoxy topcoat based on a high molecular weight epoxy resin Application as finishing coat in epoxy systems for concrete structures exposed to atmospheric land or equipment in chemical and other factories where epoxy paints are specified.

# **SPECIFICATION DATA :**

Genetic type :	Epoxy coating.			
Gloss :	High gloss			
Flash point :	23 +/- 2°C .			
Volume solids :	50 +/- 2 % depending on colour .			
Adhesion: Excellent on correctly prepared surfaces				
Chemical resistance: The fully cured coating offers outstanding resistance to aqueous solutions and a wide range				
of industrial chemicals, fat, crude oils, mild acids, etc.				
Abration resistance : Good resistance to abration and mechanical damage				
Not recommended for direct exposure to sunlight.				
Temperature: Dry service temperature range up to 120°C				

#### **COLORS:**

According to colour card

#### **RECOMMENDED USE :**

Surface preparation:

- \* All surfaces must be dry and clean
- \* The surface to be painted should be abrasive blasted to minimum SA-2.5 Swedish Standard. For optimum performance, abrasive blasting in accordance to SA -3.0
- \* Primer should be used : ZOTA ZINC RICH PRIMER, ZOTA EPON W PRIMER 99.
- \* Substrate temperature may not exceed  $50^{\circ}$ C.

Recommended no.of coats :

\* 1-2 coats

Typical Dry Film Thickness :

\* 40 microns equivalent to 80 microns wet

Theoretical Coverage :

\* 12.5 m2 / Ltr

# **DRYING TIMES:**

Drying times

es :	Temperature	Touch dry	Hard dry	Overcoating	Final Cure
	24 <sup>0</sup> C	2 Hours	10 Hours	10 Hours	8 Days
	32 <sup>0</sup> C	1 Hours	6 Hours	6 Hours	4 Days

Pot Life : 3 Hours at  $25^{\circ}$ C

# **APPLICATION:**

Method of Application :

- \* Conventional : Suitable
- \* Brush or Roller: Suitable for small erea. Care must be taken to achieve the specified dry film thickness
- \* Airless spray : Recommended

#### Mixing ratio :

- \* 4 volume part A to 1 Volume part B of ZOTA EPON FINISH 303
- \* Stir the content of the base component, continue stirring and gradually add the total content of the hardener component, continue stirring until a homogeneous mix is obtained

#### Thinner:

\* ZOTA THINNER 803

#### Cleaning solvent:

\* ZOTA THINNER 803

# **PACKAGING :**

- \* 16 Liters of part A in 20 liters container.
  - 4 Liters of part A in 5 liters container.
- \* 4 Liters of part B in 5 liters container.
- 1 Liter of part B in 1 liter container.

#### **HEALTH AND SAFETY:**

Please observe the precautionary notices displayed on the container.

Keep out reach of children.

Use under well ventilated conditions.

Wear a mask, goggles and protective equipment during the construction.

Do not inhale spray mist.

Avoid eyes and skin contact. Spillage on the skin should immediately be removed with suitable cleanser, soap water and medical attention sought immediately.

# **STORAGE:** Store in cool and dry places .